

## AN216A

2023.04.03

### SPECIFICATIONS

▶ Chemical formula:	AlN
▶ Chemical name:	Aluminium nitride
▶ Apperance:	Dense sintered aluminium nitride
▶ Main characteristics:	High electrical insulation, high thermal conductivity
▶ Main applications:	Heat uniformity parts, high temperature treatment fixtures, semiconductor processing equipment parts
▶ Colour:	Grey

### MECHANICAL & PHYSICAL CHARACTERISTICS (TYP.)

<b>Density</b>	[g/cm <sup>3</sup> ]	JIS R 1634	3.4
<b>Water absorption</b>	[%]	JIS C 2141	0
<b>Vickers hardness HV9.807N</b>	[GPa]	JIS R 1610	10.4
<b>Flexural strength 3 P.B.</b>	[MPa]	JIS R 1601	310
<b>Compressive strength</b>	[MPa]	JIS R 1608	-
<b>Young's modulus of elasticity</b>	[GPa]	JIS R 1602	320
<b>Poisson's ratio</b>	[ $\nu$ ]	JIS R 1602	0.24
<b>Fracture toughness (SEPB)</b>	[MPa*m <sup>0.5</sup> ]	JIS R 1607	-
<b>Coefficient of linear thermal expansion</b>	40 - 400 °C 40 - 800 °C	[ $\times 10^{-6}/K$ ]	4.6 5.3
<b>Thermal conductivity</b>	[W/(m*K)]	JIS R 1611	150
<b>Specific heat capacity</b>	[J/(g*K)]	JIS R 1611	0.71
<b>Thermal shock temperature difference</b>	[°C]	JIS R 1648	-
<b>Dielectric strength</b>	[kV/mm]	JIS C 2141	14
<b>Volume resistivity</b>	20 °C 300 °C 500 °C	[ $\Omega \cdot cm$ ]	$>10^{14}$ $10^{10}$ $10^8$
<b>Dielectric constant</b>	-	JIS C 2141	8.6
<b>Dielectric loss angle</b>	[ $\times 10^{-4}$ ]	JIS C 2141	3
<b>Loss factor</b>	[ $\times 10^{-4}$ ]	JIS C 2141	26

The values are typical material properties and may vary according to products configuration and manufacturing process.  
For more details, please feel free to contact us.

**KYOCERA Fineceramics Europe GmbH**

E-Mail: [info@kyocera-fineceramics.de](mailto:info@kyocera-fineceramics.de) · [www.kyocera-fineceramics.de](http://www.kyocera-fineceramics.de)

© 2023 KYOCERA Fineceramics Europe GmbH. We reserve the right to make changes without prior notice.